

Trilogy

Porcelain tiles



Scan to learn more

Size $11\frac{3}{4}" \times 23\frac{5}{8}"$
 $23\frac{5}{8}" \times 47\frac{1}{4}"$

Thickness ± 9 mm












Finish Matte

V3 MODERATE VARIATION



Field tiles	Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish	Edge
	12" x 24"	$11\frac{3}{4}" \times 23\frac{5}{8}"$	9 mm	Matte	-
	24" x 48"	$23\frac{5}{8}" \times 47\frac{1}{4}"$	9 mm	Matte	Rectified
Mosaics and coordinating trims	Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish	
	Mosaic 2" x 2"	$11\frac{3}{4}" \times 11\frac{3}{4}"$	9 mm	Matte	
	Chevron Mosaic	$14\frac{1}{8}" \times 9\frac{7}{8}"$	9 mm	Matte	
	Arabesque Mosaic	$12\frac{1}{2}" \times 12\frac{8}{9}"$	9 mm	Matte	
	Bullnose 3" x 24"	$2\frac{7}{8}" \times 23\frac{5}{8}"$	9 mm	Matte	
	Cove Base 6" x 12"	$5\frac{7}{8}" \times 11\frac{3}{4}"$	8.5 mm	Matte	

Please refer to caliber chart for working size. Close joints are not recommended.

		Requirements			
Property	Test Method	Calibrated	Rectified		
Regularity characteristics	 Nominal Size	ASTM C499	±3.00%	-3.00% ÷ +2.00%	Compliant
	Caliber Range		±0.50% or ±0.08 in (±2.0 mm) (*)	±0.25% or ±0.03 in (±0.8 mm) (*)	Compliant
	Thickness ⁽¹⁾		Range: 0.04 in (1.02 mm)		Compliant
	Wedging	ASTM C502	±0.50% or ±0.08 in (±2.0 mm) (*)	±0.25% or ±0.03 in (±0.8 mm) (*)	Compliant
	 Warpage Edge	ASTM C485	±0.75% or ±0.09 in (±2.3 mm) (*)	±0.40% or ±0.05 in (±1.3 mm) (*)	Compliant
			Warpage Diagonal	±0.50% or ±0.08 in (±2.0 mm) (*)	±0.40% or ±0.07 in (±1.8 mm) (*)
Structural characteristics	 Water Absorption	ASTM C373	≤ 0.5%		≤ 0.5%
Bulk mechanical characteristics	 Breaking Strength	ASTM C648	Average ≥ 250 lbf. (1.11 kN) Individual ≥ 225 lbf. (1.00 kN)		≥ 350 lbf. avg
Surface mechanical characteristics	 Mohs' Scratch Hardness	C1895	Subject to the project ⁽³⁾		MOHS 7-8: Hard. Suitable for high-traffic residential and light commercial areas.
Physical properties	 Bond Strength	ASTM C482	≥ 50 psi. (0.34 Mpa)		≥ 100 psi.
Thermal and hygrometric characteristics	 Resistance to Freeze/Thaw Cycling	ASTM C1026			Resistant
	 Thermal Shock Resistance	ASTM C484			Resistant
Chemical characteristics	 Chemical Resistance	ASTM C650			Unaffected
	 Stain Resistance	ASTM C1378			Unaffected
Safety characteristics	 Dynamic Coefficient of Friction (DCOF)	ANSI A326.3	Subject to the project ⁽²⁾ ⁽³⁾		≥ 0.42 Wet Interior Wet (IW) ⁽²⁾

(*) Whichever is less.

(1) Whichever is less, for tiles up to 24"x24" (610 mm x 610 mm).

(2) DCOF ≥ 0.42 Wet may not be a requirement for all projects.

(3) The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations. For updated manufacturer classification according to ANSI A326.3. Section 4 - "Product Use Categories", please refer to our website.

For more details please see the catalogue or visit atlasconcordeusa.com
The Health Product Declaration® logo is a registered trademark of HPD Collaborative.